

Description

Bostik Simson ISR 70-08 AP is a high quality Silyl Modified Polymer (SMP) based Direct Glazing Adhesive especially developed for the rapid and efficient bonding of windscreens in the Auto Aftermarket as well as in OEM, Bus, Coach & Train building and other areas of the Transport market, especially where vehicles have to be released (or moved) shortly after installation.

Features

- Bostik Simson ISR 70-08 AP combines the advantages of desired properties of structural sealants including polyurethanes. **Simson ISR 70-08 AP is not reliant on the primed system to provide a cross-linking covalent bond (less chances of applicator error).**
- Immediately after installation the product has a high Green Strength (a high internal strength), which results in a heavy paste with an extremely good slump resistance. Reaction starts with moisture and results in an irreversible vulcanized adhesive. The high green strength coupled to the high tack results in rapid bonding and makes the product very suitable for those applications where the vehicles have to be released (or moved) shortly after installation.
- Bostik Simson ISR 70-08 AP adheres well without black glass primer on glass and no UV resistant primer is needed when the glass adhesive interface is adequately UV-protected by a ceramic coating.
- **Solvent-isocyanate- and PVC free.**
- Excellent UV resistance and ageing properties.
- Excellent temperature resistance, permanent elastic within temperatures from -40°C till +120°C.
- No odour
- Paintable
- Very low electrical conductivity. Suitable for use with window aerials
- Prevents contact corrosion on aluminium substrates
- Non staining – less than 1% carbon black content
- Possible reduced or no clamping required

Recommended Uses

- Bostik Simson ISR 70-08 AP is specially designed for the rapid replacement of windscreens.
- At 23°C and 50% relative humidity.



ONE HOUR DRIVE AWAY IN VEHICLES WITH DUAL AIRBAGS*

MEETS U.S. SAFETY STANDARDS
FMVSS212 WINDSHIELD RETENTION TEST
FMVSS208 OCCUPANT CRASH PROTECTION TEST

Application Instructions

Surface Preparation

a. Replacement Fixed Glass

Preparation of a window with black ceramic band:

1. Ensure the surface of the glass is clean and dry, dust and grease free.
2. Cleaning of the ceramic coated layer can be done with Simson 'wash' Prep M (a one step treatment).
3. Use clean, lint and colour free cotton cloth to wipe the bond area with **Simson Prep M**. **Important Note:** Don't use Simson Prep M that has a milky appearance.
4. Let dry for approximately 5 minutes before you continue with the application of the adhesive.

Preparation of a Window without Black Ceramic Band:

1. Ensure the surface of the glass is clean and dry, dust and grease free. Use a clean, lint and colour free cotton cloth, wet with **Bostik N40 Primer** to wipe the surface of the bond area, leaving a very thin film (discard cotton cloth), then rub the surface with a clean, lint and colour free cotton cloth using a buffing action. Drying time of the film is 3-5 minutes.
2. **Important Note:** Don't use any activator that has a milky appearance.
3. Shake Simson Prep G Extra bottle thoroughly for at least 30 seconds or more.
4. Open bottle: **Important Note** – Don't use any primer that has gelled or separated.
5. Apply primer, with a clean dry dauber, evenly in one pass, onto the prepared bond area surface to give a continuous primer film. Leave to dry for 10 minutes.
6. The primed area must be covered by **Simson ISR7008AP** within 3 hours. If it is not applied within 3 hours, reapply the **Simson Prep G Extra** as per above, starting with instruction 2.

Preparation of the Body:

Preparation of a freshly painted metal-flange:

1. Ensure the surface of the freshly painted metal-flange is clean, dry, dust and grease free.
2. Use a clean, lint and colour free cotton cloth to apply **Simson Prep M** to the surface of the freshly painted flange, leaving a very thin film.
3. Let dry for approximately 5 minutes.

Repair of damaged paint layer:

1. Ensure the surface of damaged paint layer is clean and dry, dust and grease free.
2. Shake **Simson Prep G Extra** Bottle thoroughly for at least 30 seconds or more, open bottle and apply **Simson Prep G Extra** onto damaged area with a dauber.
3. Ensure that no primer is applied to the freshly cut adhesive!
4. Leave to dry for 10 minutes before applying the adhesive or before installing the windscreen with adhesive.

b. Application of Bostik Simson ISR 70-08 AP

Extrude a minimum 9x9 mm triangular bead of Simson 70-08 AP onto the bond area (between the dam of closed cell double sided polyethylene foam tape and the edge of window or the metal flange/freshly cut out old adhesive).

After extruding the Simson 70-08 AP, the window must be put into place as soon as possible to avoid any contamination and must be installed within 15 minutes.

c. Clean up after Installation

Excess material should be removed by wiping with clean dry cloth. Remaining material should be cleaned with Bostik Handi-Clean Towels or IPA (Iso propyl alcohol).

Properties

Colour/s:	Black	Curing Speed after 24hrs	approx. 3 mm (20°C/50% R.H.)
Basic Material:	Silyl Modified Polymer (SMP)	Shore A Hardness	approx. 60 (DIN 53505)
Specific gravity:	Approx. 1.5	Volume Change	<3% (DIN 52451)
Curing Method:	Moisture	Electrical Volume Resistivity	>10 ¹¹ Ωcm (DIN 53428)
Skin Forming Time:	approx. 15 min. (20°C/50% R.H.)	Tensile Stress (100%)	Approx. 2.3 MPa (DIN 53504/ISO37)
Open Time	<15 min. (20°C/50% R.H.)	Tear Propagation	approx. 16N/mm (DIN 5315/ISO34)
Tensile Stress at Break	approx. 2.9 MPa (DIN 53504/ISO37)	E-Modulus (10%)	Approx. 5.5 MPa (DIN 53504/ISO37)
Elongation at Break	approx. 250% (DIN 53504/ISO37)	Solvent Percentage	0%
Shear Stress	approx. 2.4 MPa (DIN 53283/ ASTM D1002)	Application Temperature	+5°C to +35°C
Isocyanate Percentage	0%	UV-and Weather Resistance	Very Good
Temperature Resistance	-40°C to +120°C	Chemical Resistance	Good
Temperature Resistance	+180°C (max ½ hr.)		

Storage & Shelf Life

Store in a cool, dry place, out of direct sunlight. Storage areas must be well ventilated and comply with Local, State and Federal regulations. For maximum shelf life, store between 5° and 20°C.

Shelf life is up to 12 months when stored in original, unopened containers, under the above conditions.

Health & Safety

Obtain and read Material Safety Data Sheet, for details on Health and Safety information, prior to use of the material.

Packaging

Simson ISR 70-08 AP is available in 290 ml cartridges and 600 ml sausages.

Product Details

Item Number	Size	Pack Quantity
266574	290ml Cartridge	12
266515	600ml Sausage	12

The representations and recommendations regarding the products are based on tests which we believe to be reliable. However, no guarantee of their accuracy can be made because of the great range of field conditions and variations encountered in raw materials, manufacturing equipment and methods. Thus, the products are sold with a limited warranty only, and on the condition that purchasers will make their own tests to determine the suitability of the product for their particular purposes. Under no circumstances will Bostik Australia Pty Ltd be liable to anyone except for replacement of the products or refund of the purchase price.

**ALL SALES ARE EXPRESSLY LIMITED TO THE TERMS AND CONDITIONS OF SALE OF
BOSTIK AUSTRALIA PTY LTD**

Head Office Bostik Australia Pty Ltd, 51-71 High Street, Thomastown Vic 3074
A.B.N. 79 003 893 838
Phone: (03) 9279 9333 Fax: (03) 9261 4744
Phone Industrial: Toll free 1300 560 799



Quality
ISO 9001
SAI GLOBAL

Quality endorsed ISO9001 (Thomastown site)
TS16949 (Automotive).

Product: Simson ISR7008 AP
Issue Date: September 2014
Issue No.: 2
Author: David V Stuart
Division: Industrial Adhesives
Total Pages: 4