

## Product Information Sheet

**MATERIAL ID:**

**EPO-TEK® 921**

**Date:** 08/2007

**Per:**

**Rev:** II

**Material Description:**

A two component, high Tg, electrically insulating, thermally conductive epoxy designed for thermal management applications found in semiconductor, hybrid microelectronics, PCB, and optical industries. It can be an adhesive for mounting heat sinks and substrates, a seal for many types of packages, or a thermal potting compound.

**Number of Components:**

Two

**Mix Ratio by weight:**

100:2.2

**Cure Schedule (minimum)**

150°C/5 Minutes - 120°C/10 Minutes - 100°C/20 Minutes

**Specific Gravity:**

--- Part A: 2.45 Part B: 1.02

**Pot Life:**

6 Hours

**Shelf Life:**

Six months at room temperature

*NOTE:* Container(s) should be kept closed when not in use. Filled systems should be stirred thoroughly before mixing and prior to use

**MATERIAL CHARACTERISTICS:** *To be used as a guide only, not as a specification. Data below is not guaranteed. Different batches, conditions and applications yield differing results; Cure condition: 150°C/1 hour*  
 \* denotes test on lot acceptance basis

### PHYSICAL PROPERTIES:

<b>*Color (before cure):</b>	Part A: Grey Part B: Amber	<b>Die Shear @ 23°C:</b>	≥ 20 Kg / 6,800 psi
<b>*Consistency:</b>	Smooth thixotropic paste	<b>Degradation Temp:</b>	356 °C
<b>*Viscosity (23°C):</b>		<b>Weight Loss:</b>	
@ 10 rpm	20,000 - 40,000 cPs	@ 200°C:	0.11 %
<b>Thixotropic Index:</b>	2.5	@ 250°C:	0.20 %
<b>*Glass Transition Temp:</b>	≥ 90 °C (Dynamic Cure 20—200°C /ISO 25 Min; Ramp -10—200°C @ 20°C/Min)	@ 300°C:	0.45 %
<b>Coefficient of Thermal Expansion (CTE):</b>		<b>Operating Temp:</b>	
Below Tg:	26 x 10 <sup>-6</sup> in/in/°C	Continuous:	- 55°C to + 200°C
Above Tg:	97 x 10 <sup>-6</sup> in/in/°C	Intermittent:	- 55°C to + 300°C
<b>Shore D Hardness:</b>	93	<b>Storage Modulus @ 23°C:</b>	1,036,402 psi
<b>Lap Shear @ 23°C:</b>	1,808 psi	<b>*Particle Size:</b>	≤ 50 microns

### ELECTRICAL AND THERMAL PROPERTIES:

<b>Thermal Conductivity:</b>	1.4 W/mK	<b>Dielectric Constant (1KHz):</b>	6.40
<b>Volume Resistivity @ 23°C:</b>	≥ 8 x 10 <sup>13</sup> Ohm-cm	<b>Dissipation Factor (1KHz):</b>	0.009

### OPTICAL PROPERTIES @ 23°C:

<b>Spectral Transmission:</b>	N/A	<b>Index of Refraction:</b>	N/A
-------------------------------	-----	-----------------------------	-----

EPOXY TECHNOLOGY, INC.  
 14 FORTUNE DRIVE, BILLERICA, MA 01821 (978) 667-3805, FAX (978) 663-9782  
 WEB SITE: [www.epotek.com](http://www.epotek.com)