## LORD TECHNICAL DATA

# Circalok™ 6756 Primer

#### **Description**

LORD Circalok<sup>™</sup> 6756 primer is designed for use in electronics applications to bond Room Temperature Vulcanized (RTV) silicone rubbers to most metals and glass. It may also be used to bond addition-cure RTV silicones.

#### **Features and Benefits**

**Versatile** – provides good adhesion on most RTV silicone rubbers, as well as addition-cure RTV systems.

**Durable** – provides superior hydrolytic stability.

#### **Application**

**Surface Preparation** – Thoroughly clean all bond surfaces with a solvent such as xylene, acetone or trichlorethane. Some surfaces may be cleaned with detergents, then thoroughly rinsed and dried.

**Mixing** – When not in use, a precipitate may develop in the primer container. Do not shake or mix in the precipitated portion. Remove the precipitated portion prior to primer use. Quality of primer is not affected if a precipitate occurs.

**Applying** – Apply primer by brush or spray methods. For optimum adhesion, film thickness of Circalok 6756 primer should be 3-10 micron.

**Drying** – Allow primer to air-dry for 60-90 minutes before applying the RTV silicone. When dry, Circalok 6756 primer produces a chalky film.

#### Shelf Life/Storage

Shelf life is 18 months from date of shipment when stored in a cool, dry environment at 15-35°C in original, unopened container.

Circalok 6756 primer is flammable. Do not store or use near heat, sparks or open flame.

#### **Cautionary Information**

Before using this or any LORD product, refer to the Material Safety Data Sheet (MSDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

### **Typical Properties\***

Appearance Clear or Red Liquid

Viscosity, cps @ 25°C 1
Specific Gravity @ 25°C 0.77
Flash Point, °C 10

\*Data is typical and not to be used for specification purposes.



## LORD TECHNICAL DATA

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

Circalok and "Ask Us How" are trademarks of LORD Corporation or one of its subsidiaries.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide ... Ask Us How.

LORD Corporation World Headquarters

111 Lord Drive Cary, NC 27511-7923 USA

Customer Support Center (in United States & Canada)

For a listing of our worldwide locations, visit LORD.com.

+1 877 ASK LORD (275 5673) www.lord.com

