

# Soudafoam Gun Door and Window

Revision: 08/07/2020

Page 1 from 2

## Technical data

Base	Polyurethane
Consistency	Stable foam, thixotropic
Curing system	Moisture cure
Skin formation (20°C/65% R.H.)	7-8 minutes
Drying time (20°C/65% R.H.)	Dust free after 20-25 minutes
Curing rate (20°C/65% R.H.)	30 minutes for a 1/8" bead
Yield	44 liter
Yield (ASTM C-1536) (for 750 ml)	1467 m @ 1/4" (6.4 mm) dia. bead
Shrink	None
Post expansion	None
Cellular structure	70-80% closed cells
Color	Champagne
Insulation factor	3.9 - 4.1 for 25 mm
Water absorption	1% Vol
Shelf Life	18 months
Application Temperature	5 °C – 35 °C
Service Temperature	-40 °C – 90 °C

## Product description

Soudafoam Gun Door and Window is a one-component, self-expanding, ready to use polyurethane foam, which contains HCFC- and CFC-free propellants who are not harmful for the ozonlayer and where the canister is provided with a thread so it can be used on a gun.

Sealing of all openings in roof constructions.

Apply of an acoustic baffle

Improving thermal isolation in cooling systems.

All foam applications in static joints.

Insulation of window- and door frames and window sills

Insulating around pipes and electrical wiring.

## Properties

Excellent stability (no shrinkage or post-expansion)

High filling capacity

Good adhesion on all surfaces (except PE, PP and PTFE).

High insulation value, thermal and acoustic  
Very good bonding properties.

Will not bow or bend window and door frames

Low expansion

Freon free (not harmless to ozone layer and greenhouse effect)

Not UV-resistant

## Packaging

*Color:* champagne

*Packaging:* 750 ml aerosol (net)

## Shelf life

18 months unopened and stored in dry and cool conditions (Between 5 and 25 °C), Upright storage is recommended.

## Applications

Installing of window and door frames.

Filling of cavities.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

### Address

40 Upton Road  
Ontario, Canada M1L 2B9

### Phone

416-751-3700  
(1-416-PAISLEY)

### Email

info@paisley.ca

### Website

www.paisleyproducts.com

---

## Soudafoam Gun Door and Window

---

Revision: 08/07/2020

Page 2 from 2

### Application method

Shake the aerosol can for at least 20 seconds. Fit the gun on the adapter. Surface should be free from grease and dust. Moisten surfaces with a water sprayer prior to application. For non-conventional substrates a preliminary adhesion test is recommended. Fill holes and cavities for 65 %, as the foam will expand. Repeat shaking regularly during application. If you have to work in layers repeat moistening after each layer. Fresh foam can be removed using Soudal Gun & Foamcleaner or acetone. Cured foam can only be removed mechanically or with Soudal PU-Remover.

Can temperature: +5 °C - +35 °C

Ambient temperature: +5 °C - +35 °C.

Surface temperature: +5 °C - +35 °C

### Health- and Safety Recommendations

Take the usual labour hygiene into account. Always wear gloves and goggles. Remove cured foam mechanically. Never burn away. Consult label and material safety data sheet for more information. When vaporizing (for example with a compressor), additional security measures will be required. Use only in well ventilated areas.

### Remarks

Moisten surfaces with a water sprayer prior to application. If you have to work in layers repeat moistening after each layer. For not common surfaces we recommend an adhesion test.

Not UV-resistant, cured polyurethane foam must be protected against UV exposure by overpainting, sealing with sealants (e.g. Silicones, polyurethane, acrylic or hybrid polymer) or covering.

### Standards and certificates

AAMA 812-10

ASTM C-1620

ASTM E-84

UL 723

UL 1715

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

---

#### Address

40 Upton Road  
Ontario, Canada M1L 2B9

#### Phone

416-751-3700  
(1-416-PAISLEY)

#### Email

info@paisley.ca

#### Website

www.paisleyproducts.com